

**APPROVED SOURCES
NON-CHLORIDE ACCELERATING ADMIXTURES**

<u>BRAND NAME</u>	<u>PRODUCER/DISTRIBUTOR</u>	<u>RECOMMENDED MINIMUM DOSAGE</u>	
		<u>mL/kg cementitious materials</u>	<u>fl. oz./100 lb. cementitious materials</u>
Accelguard NCA	Euclid Chemical Company	7.8	12.0
CATEXOL 2000 RHE	Axim	6.5	10.0
Daraset 400	W.R. Grace & Company	6.5	10.0
DCI	W.R. Grace & Company	See Manufacturer's Recommendation	
Lubricon NCA	W.R. Grace & Company	6.5	10.0
NCA	Fritz-Pak Corporation	1% by weight of cement*	
Plastocrete 161FL	Sika Corporation	3.9	6.0
Polarset	W.R. Grace & Company	5.2	8.0
Polychem Super	General Resource Technology	5.2	8.0
Pozzolith NC 534	BASF Admixtures, Inc.	10.4	16.0
Pozzutec 20	BASF Admixtures, Inc.	3.3	5.0
Pozzutec 20+	BASF Admixtures, Inc.	3.3	5.0
Rheocrete CNI	BASF Admixtures, Inc.	See Manufacturer's Recommendation	
Sikamax NCA	Sika Corporation	3.9	6.0
Sika Rapid-1	Sika Corporation	5.2	8.0
SikeSet NC	Sika Corporation	6.5	10.0

*Dry-powdered admixture pre-packed in water-soluble bag