

Section 4112. Intermediate Aggregate for Portland Cement Concrete

4112.01 DESCRIPTION.

- A. Crushed carbonate stone chips or pea gravel from approved sources as described in [Materials I.M. 409](#). ~~Coarse natural sand resulting from disintegration of rock through erosional processes, without addition of crushed over-sized material may be used in place of the intermediate and fine aggregate.~~
- B. For crushed limestone or dolomite chips, meet the durability class required for the coarse aggregate. Acquire uncrushed pea gravel ~~or coarse sand~~ from any PCC approved durability class gravel. When the gravel durability is lower than the coarse aggregate durability requirements, the pea gravel is not to exceed 15% of total aggregate in the mix. ~~Aggregate meeting the requirements of Section 4117 will be considered coarse sand.~~

4112.02 GRADATION.

A. ~~Intermediate Aggregate.~~

~~For gradations, intermediate aggregate is considered coarse aggregate. Meet the following gradation limits:~~

| Sieve Size | % Passing |
|--------------------|------------------|
| 1/2 inch (12.5 mm) | 95-100 |
| No. 8 (2.38 mm) | 0-10 |

B. ~~Coarse Sand.~~

~~Meet the following gradation limits:~~

| Sieve Size | % Passing |
|--------------------|------------------|
| 1/2 inch (12.5 mm) | 100 |
| 3/8 inch (9.5 mm) | 90-100 |
| No. 4 (4.75 mm) | 75-95 |
| No. 8 (2.36 mm) | 60-90 |
| No. 30 (600 µm) | 10-60 |
| No. 200 (75 µm) | 0-1.5 |

Intermediate aggregate shall meet the requirements for gradation No. 2 of the Aggregate Gradation Table, [Article 4109.02](#).

4112.03 QUALITY.

A. Intermediate Crushed Stone.

Meet the requirements of Table 4112.03-1:

Table 4112.03-1: Aggregate Quality

| Aggregate Quality | Maximum Percent Allowed | Test Method |
|-------------------------------------------------------------------------------------------------------|-------------------------|--------------------------------------------------------|
| Alumina ^(a) | 0.5 | Office of Materials Test Method No. Iowa 222 |
| A Freeze | 6 | Office of Materials Test Method No. Iowa 211, Method A |
| Clay Lumps and Friable Particles | 0.5 | Materials I.M. 368 |
| ^(a) If the Alumina value fails, determine the A Freeze value for specification compliance. | | |

B. Pea Gravel and Coarse Sand.

- For the portion of coarse sand passing the No. 4 (4.75 mm) sieve, meet the quality requirements of Section 4110.
- For pea gravel and the portion of coarse sand retained on the No. 4 (4.75 mm) sieve, meet the quality requirements of Table 4112.03-2:

Table 4112.03-2: Maximum Permissible Amounts of Objectionable Materials

| Objectionable Materials. | Maximum Percent Allowed | Test Method |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------|----------------------------------------------|
| Coal and carbonaceous shale | 0.5 | AASHTO T 113 |
| Total of all shale, similar objectionable materials, coal and iron combined | 1.0 | AASHTO T 113 |
| Organic Materials, except coal | 0.01 | Office of Materials Test Method No. Iowa 215 |
| Unsound chert particles retained on 3/8 inch (9.5 mm) sieve (Nonstructural concrete) | 3.0 | Materials I.M. 372 |
| Unsound chert particles retained on 3/8 inch (9.5 mm) sieve (Structural concrete) | 2.0 | Materials I.M. 372 |
| <p>Note: Chert particle which break into three or more pieces when subjected to the freezing and thawing test will be considered unsound.</p> <p>Chert in aggregate produced from limestone sources is defined as unsound when any of the fractions of the crushed or uncrushed chert do not meet the soundness requirements.</p> | | |