

April 15, 2008 Supersedes October 15, 2005 Matls. IM 509

## TANK MEASUREMENT & ASPHALT BINDER CONTENT DETERMINATION

## <u>GENERAL</u>

This Instructional Memorandum covers the procedures used by the contracting authority to determine: (1). The quantity of asphalt binder incorporated in a project, and (2) the asphalt binder content of individual production runs of asphalt mixtures. This IM also provides instruction for completing Form #E216 (#M216). The plant inspector is referred to the applicable specifications and instructions for the specified tolerances and measurement frequencies.

Tables are furnished for computing quantities of materials stored in standard horizontal cylindrical tanks, and for correcting volumes to standard temperature. The plant inspector is responsible for checking to see that appropriate gauging tables and calibrated sticks are available prior to beginning work on a project. The contractor is required to furnish the calibrated measuring sticks, and gauging tables, for all storage tanks.

## PROCEDURES

Refer to example, Form #E216 (#M216)

## PROJECT NO.

Enter the project number listed on the project plans.

## CONTRACT ID

Enter the county listed on the project plans.

## <u>DATE</u>

Enter the date the tank measurement is recorded.

#### REPORT NO.

Enter the report number of the Daily HMA Plant Report, which reflects the daily virgin asphalt binder tank stick information.

# START OF PERIOD

## TANK NO., TANK IDENTIFICATION

Each asphalt binder storage tank shall be identified by a number or letter and listed on the form. If a separate working tank or surge tank is provided, it will be necessary to establish a uniform procedure for determining the quantity or level or material in the tank. It is recommended that the plant inspector arrange with the contractor to maintain a uniform storage level in the surge tank.

Enter the tank number for each tank being used each day of production. Four tanks may be used on a given day and recorded on a single sheet.

## TIME

Enter the beginning time for each tank that is measured each day of production.

## TANK CAPACITY (A)

The capacity of each tank depends upon its dimensions. The capacity of standard cylindrical tanks may be computed by determining the length and radius from actual measurements. All dimensions must be inside measurements. The volume of a cylindrical tank is obtained by multiplying the length of the tank (L), by the radius of the tank (½ the diameter) squared, by the constant pi (3.141592). That is, volume (V) =  $L(pi)r^2$ . When measurements are obtained in meters, convert m<sup>3</sup> to liters by multiplying by 1,000. When measurements are obtained in feet, convert ft.<sup>3</sup> to gallons by multiplying by 7.48 gal./ft.<sup>3</sup>. The contractor is required to furnish the manufacturer's data for nonstandard tanks. The contractor should not be permitted to allow the level of the asphalt cement to drop below the level of the heating coils, because accurate measurements cannot be made when the cross section of the storage area varies.

Enter the tank capacity in gallons (liters) for each tank being used each day of production.

## OUTAGE (PERCENT OF DIAMETER) (B)

The number entered in this row is obtained from the actual tank measurement using the calibrated stick provided for each tank. The measurement is made by placing the stick through the designated tank hatch down to the level of the stored material. The percent outage is read from the stick at the reference elevation, which is normally the inside shell wall. The reference elevation can be checked by placing the stick at the full elevation and checking to see that the zero percentage line and the top of the tank coincide. When the tank shell is full, the outage percentage is zero, and when the tank is empty the outage is 100%.

When non-standard tanks are used, the manufacturer's tables, measuring sticks, and instructions must be followed.

Enter the outage tank stick reading for each tank when the T104 tables are used. If a direct reading measurement is made for a tank stick reading, leave this row blank.

## INNAGE (PERCENT OF CAPACITY) (C)

Enter the FILLED PERCENT OF CAPACITY figure from the T104 tables, which coincides with the Outage (Percent of Diameter) (B) figure listed above for each tank used. If a direct reading measurement is made for a tank stick reading, leave this row blank. Refer to the manufacturer tables for non-standard tanks.

#### DIRECT READING (D)

Enter the direct reading measurement figure that is calculated for each tank being used. If you do not use a direct reading tank measurement stick, leave this row blank.

## TEMPERATURE (E)

The temperature of the asphalt binder in each tank must be determined at the time the measurements are made. This is done by lowering a maximum registering thermometer to the approximate center of the asphalt cement stored. The thermometer must be shook down to a temperature less than that of the asphalt cement in the storage tank and must be allowed to adjust to the temperature of the stored material. From 3 to 5 minutes should be allowed for this adjustment. Thermometers mounted permanently in the storage tanks by the manufacturers may be used if they agree with the thermometers checked by the Central Laboratory.

Enter the Fahrenheit (Celsius) temperature at the time each tank is measured.

## T102 TEMPERATURE CORRECTION FACTOR (F)

The volume of asphalt in the tank at the time of measurement must be corrected to 60°F (15°C). Refer to tables T102 or T103 to obtain the appropriate four-digit correction factor which corresponds to the Celsius (Fahrenheit) temperature recorded for each tank used.

# CORRECTED GALLONS (LITERS) (G)

Enter the corrected gallons (liters) at 60°F (15°C) for each tank being used by multiplying rows A, C, & F or D & F, depending on which method is used to measure the asphalt. Divide result by 100 when C is expressed as a whole number percent. This is the standard temperature at which pay quantities are determined.

## TOTAL CORRECTED GALLONS (LITERS) (H)

Enter the total corrected gallons (liters) by adding the corrected gallons (liters) figures for each tank being used.

## TOTAL ASPHALT BINDER ADDED

## TOTAL POUNDS (KILOGRAMS) (I)

This space provides for entering the total quantity of asphalt added during the production run. Care must be exercised to ensure that weight (mass) tickets are obtained for each load placed in the storage tank during the production run. Each shipment ticket should be logged in the plant book, with the appropriate date and unloading time. The weight (mass) is converted to corrected gallons (liters) at 60°F (15°C) by dividing by the weight (mass) per gallons (liters) coefficient provided by the supplier. Quantities added shall be certified or determined at the job site.

Enter the total pounds (kilograms) added to each tank being used.

## WEIGHT (MASS) PER GALLON (LITER) (J)

The asphalt binder supplier provides the average weight (mass) per gallon (liter). If asphalt binder from different sources has been used during the production run, it is necessary to compute a weighted average weight (mass) per gallon (liter) for the total quantity used. If emulsified asphalt or cutback asphalt is being used, it is necessary to reduce the mass of the diluted material to asphalt residue. The quantity of asphalt residue incorporated is determined by multiplying the total mass of emulsion or cutback by the percent residue value furnished by the supplier.

Enter the weight (mass) per gallon (liter) listed on the shipment tickets. The weight (mass) per gallon (liter) cannot change on a given day of production.

## TOTAL CORRECTED GALLONS (LITERS) (K)

Enter the total corrected gallons (liters) added during the day by adding the (I) row figures together and dividing by the (J) figure.

## END OF PERIOD

## <u>TIME</u>

Enter the ending time for each tank that is measured each day of production.

## TANK CAPACITY (L)

Enter the tank capacity in gallons (liters) for each tank being used each day of production.

## **OUTAGE (PERCENT OF DIAMETER) (M)**

Enter the outage tank stick reading for each tank when the T104 tables are used. If a direct reading measurement is made for a tank stick reading, leave this row blank.

## INNAGE (PERCENT OF CAPACITY) (N)

Enter the FILLED PERCENT OF CAPACITY figure from the T104 tables which coincides with the Outage (Percent of Diameter) (B) figure listed above for each tank used. If a direct reading measurement is made for a tank stick reading, leave this row blank.

## DIRECT READING (O)

Enter the direct reading measurement figure that is calculated for each tank being used. If you do not use a direct reading tank measurement stick, leave this row blank.

## TEMPERATURE (P)

Enter the Fahrenheit (Celsius) temperature at the time each tank is measured.

## T102 TEMPERATURE CORRECTION FACTOR (Q)

The volume of asphalt in the tank at the time of measurement must be corrected to 60°F (15°C). Refer to tables T102 or T103 to obtain the appropriate four-digit correction factor which corresponds to the Fahrenheit (Celsius) temperature recorded for each tank used.

# CORRECTED GALLONS (LITERS) (R)

Enter the corrected gallons (liters) at 60°F (15°C) for each tank being used by multiplying rows L, N, & Q or O & Q, depending which method is used to measure the AC. Divide result by 100 when C is expressed as a whole number percent. This is the standard temperature at which pay quantities are determined.

## TOTAL CORRECTED GALLONS (LITERS) (S)

Enter the total corrected gallons (liters) by adding the corrected gallons (liters) figures for each tank being used.

# CALCULATIONS

## TOTAL CORRECTED GALLONS (LITERS) USED (T)

Enter the total corrected gallons (liters) used each day of production by adding (H) and (K), then subtracting (S).

## WEIGHT (MASS) PER GALLON (LITER) (U)

Enter the four-digit figure listed in the (J) row from above.

## TOTAL POUNDS (KILOGRAMS) OF BINDER USED (V)

This number is obtained by multiplying (T) by (U).

## TOTAL POUNDS (KILOGRAMS) OF MIX PRODUCED (W)

Enter the total pounds (kilograms) of mix produced by the plant each day.

The total pounds (kilograms) of mixture are determined by adding the net weight (mass) of all the scale tickets. This total includes all mixture produced, including rejected, wasted, or commercial loads. Mixtures, such as cold mixes, which contain moisture, must be corrected for the moisture content.

## TOTAL POUNDS (KILOGRAMS) OF MIX WASTED (X)

Enter the total pounds (kilograms) of mix wasted during the day. This figure includes road waste, plant waste and other mix, which was wasted, sold rejected or otherwise disposed of. All mix so wasted should be weighed, if at all possible. It may be necessary to estimate small quantities of waste in some cases.

## TOTAL POUNDS (KILOGRAMS OF BINDER WASTED (Y)

This number is determined by multiplying the percent asphalt (Z) by the total pounds of mix wasted (X). This quantity will not be included in the project pay quantity total.

## NET TONS (MEGAGRAMS) OF ASPHALT BINDER INCORPORATED IN THE PROJECT

This is the net quantity of asphalt binder for which the contractor is eligible to receive pay.

This number is obtained by subtracting (Y) from (V) and then dividing by 1000 for Megagrams or 2000 for Tons. **THIS FIGURE SHALL BE GIVEN TO THE ROAD INSPECTOR EACH DAY.** 

#### NET TONS (MEGAGRAMS) OF MIX INCORPORATED IN THE PROJECT

This number is obtained by subtracting (X) from (W) and then dividing by 2000 for Tons or 1000 for Megagrams. This is the net quantity eligible for payment. **THIS FIGURE SHALL CORRELATE WITH THE ROAD FIGURE EACH DAY.** 

## PERCENT VIRGIN ASPHALT BINDER, BY TANK MEASUREMENT (Z)

This percent virgin binder is obtained by dividing (V) by (W) and multiplying by 100.

This percentage is obtained by dividing the total net pounds (kilograms) of asphalt binder incorporated (V) by the total net pounds (kilograms) of mix produced (W). The plant inspector is, at this point, directed to refer to appropriate specifications to determine if this percentage is within the allowable tolerance.

## **COMMENTS**

Self-explanatory:

ALL COMPUTATIONS SHOULD BE CHECKED THOROUGHLY AND PROMPTLY; ANY CORRECTIONS SHOULD BE REPORTED TO THE CONTRACTOR AND RECORDED ON THE DAILY REPORT FORMS. UPON COMPLETION OF THE PROJECT THE COMPLETED FORM SHALL BE INCORPORATED IN THE RESIDENT OR COUNTY ENGINEER PROJECT FILE.

# April 15, 2008 Supersedes October 18, 2005

Rev 11/07					Form E216
DAILY	VIRGI	N ASPHALT BINDER	R TANK MEASURE	MENT SHEET	
		-		Date:	
Contract ID.:		-		Report No.:	
			Start O	f Period	
Tank	No.:				
Т	ime:				
Tank Capacity ( Gallons )	(A):				
Outage (% of Diameter)	(B):				
T-104 Innage (% of Capacity)	(C):				
Direct Reading ( Gallons )	(D):				
Temp. °F	(E):				
T-102 Temp. Corr. Factor	(F):				
Corrected Gallons = (A*C/100*F)or(D*F)	(G):				
Total Corrected Gallons = (G+G+G+G)	(H):		_		
			Total Asphalt	Binder Added	
Total Pounds	(I):				
Weight Per Gallon	(J):				
Total Corrected Gallons = (I+I+I+I/J)	(K):				
			End Of	Period	
т	ïme:				
Tank Capacity (Gallons)	(L):				
Outage (% of Diameter)	(M):				
T-104 Innage (% of Capacity)	(N):				
Direct Reading ( Gallons )	(O):				
Temp. °F	(P):				
T-102 Temp. Corr. Factor	(Q):				
Corrected Gallons = (L*N/100*Q)or(O*Q)	(R):				
Total Corrected Gallons = (R+R+R+R)	(S):				
		Calculations			
Total Corrected Gallons Used = (H+K-S)	(T):				
Average Weight Per Gallon	(U):				
Total Pounds Of Binder Used = $(T^*U)$	(V):				
Total Pounds Of Mix Made	(W):				
Total Pounds Of Mix Wasted	(X):				
Total Pounds Of Binder Wasted = (X*Z / 100)	(Y):		_		
Net Tons Of Binder Used On Road = (( V-Y ) / 20	00 ):		_		
Net Tons Of Mix Used On Road = (( W-X ) / 20	00 ):				
Percent Virgin Binder by Tank Stick = ((V / W) * 100)	(Z):				
Comments:					

Rev 11/07					Form E216
DAILY Project No : NHSN-63-9(19)2R-45	VIRGI	N ASPHALT BINDER	TANK MEASUREN	NENT SHEET	9/8/2007
Contract ID.: 45-0639-019				Report No.:	5
				· -	
			Start Of	Period	
Tank	No.:	1			
Т	ime:	6:47 AM			
Tank Capacity ( Gallons )	(A):	25,000			
Outage (% of Diameter)	(B):	15.6			
T-104 Innage (% of Capacity)	(C):	90.0440			
Direct Reading ( Gallons )	(D):				
Temp. °F	(E):	300			
T-102 Temp. Corr. Factor	(F):	0.9187			
Corrected Gallons = $(A*C/100*F)or(D*F)$	(G):	20,681			
Total Corrected Gallons = (G+G+G+G)	(H):	20,681			
			Total Asphalt	Binder Added	
Total Pounds	(I):	103,066			
Weight Per Gallon	(J):	8.5641			
Total Corrected Gallons = (I+I+I+I/J)	(K):	12,035			
			End Of	Period	
Т	ime:	6:58 PM			
Tank Capacity (Gallons)	(L):	25,000			
Outage (% of Diameter)	(M):	69.4			
T-104 Innage (% of Capacity)	(N):	25.9350			
Direct Reading ( Gallons )	(O):				
Temp. °F	(P):	295			
T-102 Temp. Corr. Factor	(Q):	0.9204			
Corrected Gallons = (L*N/100*Q)or(O*Q)	(R):	5,968			
Total Corrected Gallons = (R+R+R+R)	(S):	5,968			
		Calculations			
Total Corrected Gallons Used = (H+K-S)	(T):	26,748			
Average Weight Per Gallon	(U):	8.5641			
Total Pounds Of Binder Used = ( T*U )	(V):	229,073			
Total Pounds Of Mix Made	(W):	4,001,650			
Total Pounds Of Mix Wasted	(X):				
Total Pounds Of Binder Wasted = $(X^*Z / 100)$	(Y):				
Net Tons Of Binder Used On Road = (( V-Y ) / 20	00):	114.54			
Net Tons Of Mix Used On Road = (( W-X ) / 20	, 00	2,000.83	•		
Percent Virgin Binder by Tank Stick = ((V / W) * 100)	(Z):	5.72	1		
	. /				

Comments: Example using T-104 Tables

Rev 11/07				Form E216
DAILY VIRGI	N ASPHALT BINDER	TANK MEASURE		0/9/2006
Contract ID : 45-0639-019	-		Report No :	9/0/2000
	-			J
		Start O	f Period	
Tank No.:	1	2		
Time:	6:47 AM	10:05 AM		
Tank Capacity (Gallons) (A):	25,000	25,000		
Outage (% of Diameter) (B):				
T-104 Innage (% of Capacity) (C):				
Direct Reading (Gallons) (D):	23,450	21,075		
Temp. °F (E):	300	300		
T-102 Temp. Corr. Factor (F):	0.9187	0.9187		
Corrected Gallons = $(A^*C/100^*F)or(D^*F)$ (G):	21,544	19,362		
Total Corrected Gallons = $(G+G+G+G)$ (H):	40,906			
	Total Asphalt Binder Added			
Total Pounds (I):	103,066			
Weight Per Gallon (J):	8.5641			
Total Corrected Gallons = $(I+I+I+I/J)$ (K):	12,035			
		End Of	Period	
Time:	6:58 PM	2:25 PM		
Tank Capacity (Gallons) (L):	25,000	25,000		
Outage (% of Diameter) (M):		-		
T-104 Innage (% of Capacity) (N):				
Direct Reading (Gallons) (O):	9,750	23,560		
Temp. °F (P):	295	300		
T-102 Temp. Corr. Factor (Q):	0.9204	0.9187		
Corrected Gallons = $(L^*N/100^*Q)or(O^*Q)$ (R):	8,974	21,645		
Total Corrected Gallons = (R+R+R+R) (S):	30,619			
	<b>Calculations</b>			
Total Corrected Gallons Used = (H+K-S) (T):	22,322			
Average Weight Per Gallon (U):	8.5641			
Total Pounds Of Binder Used = (T*U) (V):	191,168			
Total Pounds Of Mix Made (W):	3,207,523			
Total Pounds Of Mix Wasted (X):	10,000			
Total Pounds Of Binder Wasted = $(X^*Z / 100)$ (Y):	596			
Net Tons Of Binder Used On Road = ((V-Y) / 2000):	95.29	•		
Net Tons Of Mix Used On Road = (( W-X ) / 2000 ):	1,598.76	1		
Percent Virgin Binder by Tank Stick = ((V / W) * 100) (Z):	5.96	1		
		I		

Comments: Example using Direct Reading

Project No.:		D	ate:	
Contract ID.:		Report	No.:	
	Start Of Period			
Tank No.:				
Time:				
Tank Capacity (Liters) (A):				
Outage (% of Diameter) (B):				
T-104 Innage (% of Capacity) (C):				
Direct Reading (Liters) (D):				
Temp. °C (E):				
T-102 Temp. Corr. Factor (F):				
Corrected Liters (G)= (A*C*F)or(D*F):				
Total Corrected Liters (H)= (G+G+G+G):				
	To	otal AC Added		
Total Kilograms (I):	ł			
Mass Per Liter (J):				
Total Corrected Liters (K)= (I+I+I+I/J):				
	<u>E</u>	nd Of Period		
Time:	·			
Tank Capacity (Liters) (L):				
Outage (% of Diameter) (M):	· · · · · · · · · · · · · · · · · · ·			
T-104 Innage (% of Capacity) (N):	1		1	
Direct Reading (Liters) (O):			1	
Temp. °C (P):				
T-102 Temp. Corr. Factor (Q):				
Corrected Liters (R)= (L*N*Q)or(O*Q):			1	
Total Corrected Liters (S)= (R+R+R+R):	·			
Calci	ulations			
Total Corrected Liters Used (T)= (H+K-S) <sup>.</sup>				
Mass Per Liter (U):				
Total Kilograms Of AC Used (V)= ( T*U)				
Total Kilograms Of Mix Made (W)				
Total Kilograms Of Mix Wasted (X)				
Total Kilograms Of $\Delta C$ Meeted (X)- (X*7):	· · · · · · · · · · · · · · · · · · ·			
$\int dt Ma Of AC Hand On Road = ((X, X, Y, 1000))$	<u> </u>			
ent virgin AC by Tank Stick (Z)= ((V / W) * 100):				
Comments:				

8/96			Form M216
DAILY V	IRGIN AC TANK M	IEASUREMENT SHEET	00100106
Contract ID : 45-0639-019			1
		Start Of Period	
Tank No.:	1		
Time:	06:30		
Tank Capacity (Liters) (A):	94,635		
Outage (% of Diameter) (B):	10.0		
T-104 Innage (% of Capacity) (C):	94.7960		
Direct Reading (Liters) (D):			
Temp. °C (E):	149		
T-102 Temp. Corr. Factor (F):	0.9183		
Corrected Liters (G)= (A*C*F)or(D*F):	82,381		
Total Corrected Liters (H)= (G+G+G+G):	82,381		
		Total AC Added	
Total Kilograms (I):	46,750		
Mass Per Liter (J):	1.0262	······································	
Total Corrected Liters (K)= (I+I+I+I/J):	45,556		
		End Of Period	
Time:	06:35		
Tank Capacity (Liters) (L):	94,635		
Outage (% of Diameter) (M):	80.0		
T-104 Innage (% of Capacity) (N):	14.2380		
Direct Reading (Liters) (O):			
Temp. °C (P):	149		
T-102 Temp. Corr. Factor (Q):	0.9183		
Corrected Liters (R)= (L*N*Q)or(O*Q):	12,373		
Total Corrected Liters (S)= (R+R+R+R):	12,373		•
	<b>Calculations</b>		
Total Corrected Liters Used (T)= (H+K-S):	115,564		
Mass Per Liter (U): _	1.0262		
Total Kilograms Of AC Used (V)= ( T*U ):	118,592		
Total Kilograms Of Mix Made (W):	2,014,080		
Total Kilograms Of Mix Wasted (X):	12,000		

 Total Kilograms Of AC Wasted (Y)= (X\*Z):
 707

 Net Mg. Of AC Used On Road = ((V-Y) / 1000):
 117.89

 Net Mg. Of Mix Used On Road = ((W-X) / 1000):
 2,002.08

 Percent Virgin AC by Tank Stick (Z)= ((V / W) \* 100):
 5.89

Comments: Example using T-104 tables.

8/96				Form M216
DAILY V	IRGIN AC TANK ME	ASUREMENT S	HEET	00/00/00
Project No.: NHSN-63-9(19)-2R-45			Date:	09/09/96
Contract ID.: 45-0639-019			Report No.:	1
		Start C	f Period	
Tank No.:	1	2		
Time:	06:30	08:00		
Tank Capacity ( Liters ) (A):	94,635	94,635		
Outage (% of Diameter) (B):				
T-104 Innage (% of Capacity) (C):				
Direct Reading (Liters) (D):	34,629	74,898		······································
Temp. °C (E):	149	149		
T-102 Temp. Corr. Factor (F):	0.9183	0.9183		· · · · · · · · · · · · · · · · · · ·
Corrected Liters (G)= (A*C*F)or(D*F):	31,800	68,779		
Total Corrected Liters (H)= (G+G+G+G):	100,579			
		<u>Total A</u>	C Added	
Total Kilograms (I):	116,782			
Mass Per Liter (J):	1.0262			
Total Corrected Liters (K)= (I+I+I+I/J):	113,800			
		End O	f Period	
Time:	06:35	05:00		
Tank Capacity (Liters) (L):	94.635	94.635	-	
Outage (% of Diameter) (M):				
T-104 Innage (% of Capacity) (N):				
Direct Reading (Liters) (0):	53,016	59,105		
Temp. °C (P):	149	149		
T-102 Temp. Corr. Factor (Q):	0.9183	0.9183		
Corrected Liters (R)= (L*N*Q)or(O*Q):	48,685	54,276		
Total Corrected Liters (S)= (R+R+R+R):	102,961			
	Calculations			
Total Corrected Liters Used (T)= (H+K-S):	111,418			,
Mass Per Liter (U):	1.0262			3
Total Kilograms Of AC Used (V)= ( T*U ):	114,337			
Total Kilograms Of Mix Made (W):	2,014,080			
Total Kilograms Of Mix Wasted (X):	12,000			
Total Kilograms Of AC Wasted (Y)= $(X^*Z)$ :	682		·	
Net Mg. Of AC Used On Road = (( V-Y ) / 1000 ):	113.66			
Net Mg. Of Mix Used On Road = (( W-X ) / 1000 ):	2,002.08			
Percent Virgin AC by Tank Stick (Z)= ((V / W) * 100):	5.68			
Comments: Example using Direct Reading.				